

# Villafärg Acrylate

**DO NOT APPLY ON WINDOW-FRAMES!**

## **Characteristics:**

Villafärg is a water-based façade paint for use outdoors on wooden, plaster, concrete and metal surfaces. This product is especially suitable for surfaces, where you already painted with acrylic-paint. On untreated surfaces, please take notice of the equivalent primer. Villafärg generates a weatherproof, lightfast and hydrophobic finish, which retains colour and gloss. *Do not apply on window-frames, doors, frames or sills!* Frames would adhere to one another because of the thermoplastic character of the acrylate.



**Good to know:** If your wood (pine, spruce, fir) is untreated and planed always start with the oil-primer „Grundolja“ followed by the adhesion-primer „Trägrund V“. Only like that your paint adheres optimally and the wood is simultaneously protected. Your advantages: This will prevent, for example, cracks, blisters and premature flaking of the paint. The color lasts much longer, so you save time, money and labor.

**Exceptions:** For roughly sawn wood, you only need the oil-primer „Grundolja“ – but not the adhesion-primer „Trägrund V“.

## **Application / My ambition is...**

### **...a coat of paint on untreated wood:**

1. Do not apply on window-frames, doors, frames or sills!  
*The surface has to be clean, dry and intact!* Otherwise brush or scrape off any loose material such as dirt or dust, then rinse everything with clean water and allow to dry the ground.
2. Then treat the wood with the oil-primer „Grundolja“ and let it dry for 1-2 days, depending on weather conditions.
3. Not later than 7 days, apply the adhesion-primer „Trägrund V“ and let it dry for 1-2 days, depending on weather conditions.
4. Then paint the first coat Villafärg.
5. Depending on weather conditions apply the second coat after 6-8 hours.

### **...a coat of paint on painted surfaces with exfoliated points:**

1. Do not apply on window-frames, doors, frames or sills!
2. Grind off the exfoliated points. After that, rinse the *whole* surface with clean water and allow to dry the ground. In case of fungal decay use our moss- and mould-remover "Alg/Mögeltvätt". *The surface has to be clean, dry and intact!*
3. On the *polished points* treat the wood with the oil-primer „Grundolja“ and let it dry for 1-2 days, depending on weather conditions. Not later than 7 days, apply the adhesion-primer „Trägrund V“ at these points and let it dry for 1-2 days, depending on weather conditions.
4. Then paint the first coat Villafärg on the *whole surface*.
5. Depending on weather conditions apply the second coat on the *whole surface* after 6-8 hours.

### **...a refreshment of a intact paint:**

1. Do not apply on window-frames, doors, frames or sills!
2. *The surface has to be clean, dry and intact!* Otherwise brush or scrape off any loose material such as dirt or dust, then rinse everything with clean water and allow to dry the ground. In case of fungal decay use our moss- and mould-remover "Alg/Mögeltvätt".
3. Then paint the first coat Villafärg.
4. Depending on weather conditions apply the second coat Villafärg after 6-8 hours. *The second layer is not necessary when the old and the new tone ist the same!*

**Please turn =>**



www.farbe-aus-schweden.de  
Tel.: +49 (0)40 54 80 12 20

# Villafärg Acrylate

**DO NOT APPLY ON WINDOW-FRAMES!**

## **Application on plaster, concrete, cement asbestos (untreated or painted):**

1. *The surface has to be clean, dry and intact!* Otherwise brush or scrape off any loose material such as dirt or dust, then rinse everything with clean water and allow to dry the ground. In case of fungal decay use moss- and mould-remover.
2. On untreated surfaces apply our ground coat "Betoprime" and let it dry for 2-4 hours. Betoprime provides the permeability of the paint and inhibits stress cracks. Then apply two layers of Villafärg with 6-8 hours drying time in between.
2. On painted surfaces apply two coats of Villafärg with 6-8 hours drying time in between - *the second layer is not necessary when the old and the new tone is the same!*

## **Application on metal (untreated or painted):**

1. *The surface has to be clean, dry and intact!* Otherwise brush or scrape off any loose material such as dirt or dust, then rinse everything with clean water and allow to dry the ground. In case of fungal decay use our moss- and mould-remover "Alg/Mögeltvätt". In case of rust, grind it off and prepare the surface with "Rostgrund V", which takes 12-24 hours to dry.
2. Then apply two coats of Villafärg with 6-8 hours drying time in between - *the second layer is not necessary when the old and the new tone is the same!*

## **Tips:**

- **Do not apply on window-frames, doors, frames or sills!**
- Avoid painting during warm or sunlit surfaces. Heat can evaporate the water too quickly which reduces the possibility of the penetration of the binder deep into the wood, with risk for bad adhesion.
- Do not paint during rain, snow, high humidity or temperatures under +12°C – please consider the temperatures at night.
- Please pay special regard to the cutting line, end-grain, nut and tongue – prime satisfably with „Grundolja“.
- If you did not consume the total volume of the bundle, close the cap carefully. Then store the closed bundle upside down and frost-free. If you removed more than 50% of the volume, better decant the rest of the paint in a smaller bundle.

## **Technical Data:**

Binder:	Acrylic	Gloss:	40 (half glossy) on planed wood, on roughly sawn wood approx. 35 (silk matt)
Consumption :	4-6 m <sup>2</sup> /l on sawn wood, 6-8 m <sup>2</sup> /l on planed wood.	Contents:	Calculated at the mixed hue: base + pigment = contents
Coating conditions:	Minimum +12°C (also at night), maximum +26°C		
Repaintable:	After 6-8 hours, depending on weather conditions		
Cleaning:	Water		
Storage time:	2 years if unopened, store frost-free, q.v. last point under "Tips"		

**Attention!!! Some tones (like many RAL-tones) have a bad opacity and UV-instability. Please ask us – we will be glad to give you informations.**