

SOLID V

Paint for wooden facades

Characteristics:

SOLID V is an opaque, water-based emulsion paint for use outdoors on wooden facades. This product is especially suitable for surfaces, where you can't find out what kind of paint your old coating is – but do not apply on wood tar and distemper-paint like "Falu Rödfärg".

Because of its highquality binder and pigmentation this paint has a excellent resistance to weathering and light and a high protection against moss and mold. Therefore Solid V is suited for wooden facades, detached houses and carports.



Good to know: If your wood (pine, spruce, fir) is untreated and planed always start with the oil-primer „Grundolja“ followed by the adhesion-primer „Trägrund V“. Only like that your paint adheres optimally and the wood is simultaneously protected. Your advantages: This will prevent, for example, cracks, blisters and premature flaking of the paint. The color lasts much longer, so you save time, money and labor.

Exceptions: For roughly sawn wood, you only need the oil-primer „Grundolja“ – but not the adhesion-primer „Trägrund V“.

Application / My ambition is...

...a coat of paint on untreated wood:

1. *The surface has to be clean, dry and intact!* Otherwise brush or scrape off any loose material such as dirt or dust, then rinse everything with clean water and allow to dry the ground.
2. Then treat the wood with the oil-primer „Grundolja“ and let it dry for 1-2 days, depending on weather conditions.
3. Not later than 7 days, apply the adhesion-primer „Trägrund V“ and let it dry for 1-2 days, depending on weather conditions.
4. Then paint the first coat SOLID V.
5. Depending on weather conditions apply the second coat after 1 day.

...a coat of paint on painted surfaces with exfoliated points:

1. Grind off the exfoliated points. After that, rinse the *whole* surface with clean water and allow to dry the ground. In case of fungal decay use our moss- and mould-remover "Alg/Mögeltvätt". *The surface has to be clean, dry and intact!*
2. On the *polished points* treat the wood with the oil-primer „Grundolja“ and let it dry for 1-2 days, depending on weather conditions. Not later than 7 days, apply the adhesion-primer „Trägrund V“ at these points and let it dry for 1-2 days, depending on weather conditions.
3. Then paint the first coat SOLID V on the *whole surface*.
4. Depending on weather conditions apply the second coat on the *whole surface* after 1 day.

...a refreshment of a intact paint:

1. *The surface has to be clean, dry and intact!* Otherwise brush or scrape off any loose material such as dirt or dust, then rinse everything with clean water and allow to dry the ground. In case of fungal decay use our moss- and mould-remover "Alg/Mögeltvätt".
2. Then paint the first coat SOLID V.
3. Depending on weather conditions apply the second coat SOLID V after 1 day. *The second layer is not necessary when the old and the new tone ist the same!*

Please turn =>



www.farbe-aus-schweden.de
Tel.: +49 (0)40 54 80 12 20

SOLID V

Paint for wooden facades

Tips:

- Avoid painting during warm or sunlit surfaces. Heat can evaporate the water too quickly which reduces the possibility of the penetration of the binder deep into the wood, with risk for bad adhesion.
- Do not paint during rain, snow, high humidity or temperatures under +8°C – please consider the temperatures at night.
- If you want to treat your wood indoor (e.g. garage, cellar), please apply very thin layers according to the drying time in between. Provide for light and ventilation, otherwise the paint needs much longer to cure.
- Please pay special regard to the cutting line, end-grain, nut and tongue – prime satially with „Grundolja“.
- If you did not consume the total volume of the bundle, close the cap carefully and store the closed bundle upside down. If you removed more than 50% of the volume, better decant the rest of the paint in a smaller bundle.

Technical Data:

Binder:	Alkyd and Acrylic	Gloss:	40 (half-matt) on planed wood, on roughly sawn wood approx. 25 (silk matt)
Consumption :	6-9 m ² /l on sawn wood, 9-11 m ² /l on planed wood.	VOC:	(Kat A/d) 130 g/l (2010)
Coating conditions:	Minimum +8°C (also at night), maximum +26°C	Contents:	Calculated at the mixed hue: base + pigment = contents
Repaintable:	After 1 days, depending on weather conditions		
Cleaning:	Water		
Storage time:	2 years if unopened, store frost-free, q.v. last point under “Tips”		

Attention!!! Some tones (like many RAL-tones) have a bad opacity and UV-instability. Please ask us – we will be glad to give you informations.