



DATA SHEET

TEXAL GOLVFÄRG

Area of use

Solventbased pigmented floor enamel, suitable for e.g. wood-surfaces, concrete, or linoleum indoors. Also as a strong glossy enamel for carpentries, furniture, skirting-board and metalsurfaces both in- and outdoors.

Special properties

Texal Golvfärg is based on urethan alkyd resins which are hard and flexible at the same time. It has good adhesion, scratch- and chemical resistans, and can handle alkali and most used household chemicals. Low yellowing-tendency and leaves a glossy surface which is easy to clean. Is a part of Colorex-MIX tinting system.

How to use

Wood in- and outdoor: Use Universallack as ground indoor and Utegrund outdoor. Finish with 2 layers Texal Golvfärg undiluted. *Steel and iron:* Surface is cleaned and eventual rust is steel-brushed. Ground-coat Rostskyddsprimer and apply Texal Golvfärg 2 times undiluted. *Concretefloor:* Fresh concrete has to dry some months before treatment. As groundcoat apply Texal Universallack diluted with 30-50% white spirit. Apply 2 times Texal Golvfärg. An even stronger floor is achieved by applying 1 coat Texal Universallack (with or without flakes) on top of Texal Golvfärg. *Aluminium:* Surface has to be mat-sanded and groundcoated with 2-komponent epoxypaint. As topcoat apply Texal Golvfärg 2 layers undiluted.

Technical Data

Resin:	Urethanalkyd resin	YSAM-gr./YL-gr.:	2/00
Gloss:	80-90 glossy (depends on number of layer and substrate) acc. SS-184184	Viscosity:	340 cP
Density:	1,11 acc. to SS-184111	Flammable:	2b, flashpoint +40°C
Solid content:	45 volume-%	Storage time:	2 year in unopened can
Thinner/Cleaning:	White spirit	Application:	Brush, roller or spraying
Drying time:	4 hour touchdry 18 hour repaintable 2-3 days final hardness depending on temperature and humidity	Colour:	White/Base A, Base B/C, light grey
Washability:	> 10.000 laps acc.SS-184164	Packaging:	1, 2.5 and 10
		Fillingdegree:	White/Base A 94%, Base B/C 90%
		Application temp.:	Minimum + 4°C
		Covering:	8-12 m ² /lit