



MÄSTARLACK 40/70

WATERBORNE ACRYLIC INDOOR ENAMEL

Product type

Waterborne acrylic halfglossy and glossy enamel meant for finishtreatment on carpentry-surfaces indoor.

Application

Specially aimed as finishtreatment with beush, spraying or roller indoor on carpentry, rails, furniture, doors etc.

Special properties

Mästarlack enamel is in accordance with highest demands on nice flow and gloss, good resistance and hardness. Easy to apply and work with. On doors or similar big surfaces Mästarlack can be applied with roller. The enamel has good adhesion and is totally non-yellowing. Can be sprayed after diluting with 5-10% water. It is a part of Colorex-MIX tinting system.



Application data sheet

Surface preparation

The substrate which shall be painted shall be clean, with good adhesion, dry and dustfree. Wash, flush and remove old paint with bad adhesion. Glossy surfaces shall be sanded mat. Uneven surfaces shall be treated with putty and sanded and wiped clean before overpainted with Mästargrund.

Application

The paint is ready to use. Apply with brush or suitable enamel-roller. After light diluting with water, it can also be applied by spraying. When applying tinted paint always try to apply complete areas with paint from the same can. Recommended is 1-2 layer, depending on type and colour of surface which shall be painted.

Coating conditions

Apply under controlled conditions, where air-, paint- and surfacetemperature never may be below +5°C. At very high humidity dryingtime will be longer.

Technical data

Covering	Depending on type of surface, 6-10 m ² /liter
Resin	Acrylic/Styrolacrylic
Solid content	40 % pro volume
Density	1,3 kg/liter
Viscosity	280 cP
Thinner/cleaner	Water
Application	Brush, roller or spraying
Drying time (it is advisable to indicate the temperature and humidity, at which the data are presented)	Touch dry/repaintable 3 hour Repaintable 12 hours Totally dry 3-4 days At 20°C and max 85% humidity
Gloss	35-40 halfglossy, 65-70 glossy, measured at Gardner 60°
Colour	White Base A
Washability	10.000 laps according ISO 6504-3. Class 1 acc. DIN 13399
Storage time	2 year in unopened can, frostless
Packaging	2,7L, 0,9L

Eco – signs

Individual safety

Avoid skin and eye contact and inhalation of dust and spray mist.

Environmental protection

Do not allow into drains or water courses.
Dispose in accordance with regulations from authorities